

## **MAC STUD E74**

## **Description & Applications:**

Flux coated Manual Metal Arc electrode for cutting all metals using standard MMA equipment. Will cut all steels including stainless – also non ferrous cast irons and nickel based alloys.

## Related Specification:

There is no national or international specification existing for Mac Cut E74.

# Typical All weld Metal Mechanical Properties :

Not Applicable.

#### Current:

AC (OCV 70 min) or DC+.

## Sizes Available and Recommended Amperages:

2.50mm 3.25mm 4.00mm 5.00mm 90-140 130-190 200-280 280-350

## Storage:

If allowed to become damp the electrodes should be re-dried for one hour at 150°C before use.